KANSAI PAINT

PAR WEATHERCOAT

100% ACRYLIC EXTERIOR WALL EMULSION

100% ACRYLIC EXTERIOR WALL EMULSION	
PRODUCT NAME :	PAR WEATHERCOAT
DESCRIPTION:	PAR Weathercoat by Kansai is a 100% pure acrylic, high performance, superior quality exterior grade emulsion that gives a brilliant smooth and ultra luxurious finish. Specially formulated to withstand the harsh tropical climate, PAR Weathercoat is formulated to last longer than ordinary emulsion paint. PAR Weathercoat comes with a written 6 years protection warranty against flaking, peeling, excessive colour fading, fungi and algae growth
	Approved by SIRIM to Malaysian Standards MS134:2007.
DESIGNED USE :	For use on new or previously painted exterior masonry surfaces such as brickwork, plaster, cement rendering and asbestos where performance of up to 6 years protection is required.
BINDER TYPE :	Premium grade 100% pure acrylic binder pigmented with chalk resistant titanium dioxide and other high grade pigments that resist salts in new mortar, cement rendering and other surfaces.
PERFORMANCE:	 6 Years Performance Warranty. 100% acrylic resins - outlast ordinary emulsion. Excellent fungal and algae growth resistance. Excellent colour retention. Tough synthetic finish - washable. No added lead or mercury.
PHYSICAL PROPERTIES: Coverage* Volume Solids Dry Film Thickness Wet Film Thickness Flash Point	10 – 12 m²/Lt @ 25 microns White 40%, other colours will vary 25 microns / coat 63 microns / coat Not applicable
FINISHING : Colours Finish Pack Size	See PAR by Kansai Colour Book. Smooth sheen finish. 5 & 20 litres.
APPLICATION: Drying Times Dilution	Surface dry : 10 min ; Recoat : 1 - 2 hours. Clean household water.
Cleaning Up	Clean household water.
DILUTION RATIO: Brush or Roller Conventional Spray Airless Spray	Ready for use. If dilution is required, add up to 5% clean water. Dilution up to 10% water. Ready for use.
SPRAY EQUIPMENT GUIDE : Conventional Spray Airless Spray	A typical set up would be a minimum atomising pressure of 2.8 kg/cm² and fluid pressure of 0.4 kg/cm³ with a nozzle size of 0.43 mm. A typical set up would be a minimum of 155 kg/cm³ with nozzle size of 0.38 - 0.43 mm and a spray tip angle of 65°.









KANSAI PAINT

PAR WEATHERCOAT

100% ACRYLIC EXTERIOR WALL EMULSION

SURFACE PREPARATION

New, unpainted surfaces

Allow surfaces to cure and dry out at least 28 days. Large cracks must be repaired with cement: sand mix and rendered smooth. Make good all minor defects with appropriate exterior grade fillers. Remove all loosely adhering residues by thorough brushing.

Repainting

Check for fungus and algae growth. If present, treat the surfaces with fungicidal wash by brushing onto the surface with bleach mix (1 part household bleach with 3 parts water). Allow the mixture to penetrate the affected surface. Make good all defects with appropriate patching materials. When dry, remove all fungi, algae, chalk, loosely adhering contaminants by using high pressure water-jetting. Check for powders - if present, the surface must be sealed with a coat of PAR Plasterseal 1001 solvent base wall sealer.







RECOMMENDED PAINT SYSTEM

New, unpainted surfaces



Repainting



NB: PAR Primer Sealer DPP 1035 and PAR Plasterseal DPP 1001 work best on surfaces with a moisture content of below 15% and alkalinity below pH-9, otherwise premature paint failure may occur.

SAFETY & HEALTH INFORMATION

- Ensure adequate lighting and ventilation during application and drying.
- This product does not contain added lead or mercury.
- When applying paints, it is advisable to wear eye protection.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical
- Use soap and water to remove splashes from skin.
- Storage: Keep container closed and store in clean and dry conditions.
- Do not empty into drains or water courses.
- This product is not flammable. Keep out of reach of children.
- Chemical Safety Data Sheet (CSDS) is available upon request.









For further information on Product Data, please contact: **Decorative Sales Department** Kansai Paint Asia Pacific Sdn. Bhd. (705919-W) (formerly known as Kansai Coatings Malaysia Sdn. Bhd.)

9-1 & 9-2, Level 9, Port Tech Tower, Jalan Tiara 3/KU1, Bandar Baru Klang, 41150 Klang, Selangor Darul Ehsan, Malaysia.

Tel: 6(03) 3002 4001 Fax: 6(03) 3002 4002

The information in this technical data sheet is given to the best of our knowledge based on laboratory testing and practical experience and is provided as a general advice only. No guarantee of results is implied since the conditions of use are beyond our control. It is the responsibility of the users to ensure the suitability and proper usage of the product. We reserve the right to change the data without prior notice.

^{*} Practical coverage will vary according to the roughness and porosity of surface to be painted, the application method and condition, dry film thickness and the skill of applicator.